



Test Report

Test Report No.:28010001

Issue Date : 07/03/22(DD/MM/YY)
Date(s) of testing : 25/02/22 to 07/03/22
Sample Receive Date : 25/02/22

Client Information:

Supplier No. : 50068
Client Company Name : ANHUI ANLI MATERIAL TECHNOLOGY CO.,LTD
Contact Address : DEVELOPMENT AREA of TAOHUA INDUSTRIAL
ZONE ,ECONOMY&TECHNOLIGY DEVELOPMENT
AREA,HEFEI,ANHUI,CHINA 230093

Client Contact Person : Hu Zhaoyang
IKEA Contacts Person : Jasen Xiang


The following information is provided by the applicant and who is responsible for its authenticity:

Article No. : /
Article Name : /
Article Production Date : /
Material Producer : /
Material Description : Ecological Leather
Material Batch Number/Production Date : /
Test Type : Verifying Test
Identification Code : /
Treatment : Non-FR Treated
Requirement : Level 1
Gloss in TED : /
Thickness in TED : /
Article colour name : blue
Care Label : /
Sample Description : Ecological Leather(surface)
Additional Information : /

Layer Information:

Information By Lab : /





Test Item:

Rating

1. IOS-MAT-0079, Maintainability

Pass

Remark:

"Inconclusive": combined with the expanded uncertainty, unable to rate the result due to the result both in and out of the limit.

"/": unable to rate the result due to no limit offered or test result is N.A. / N.T. /N.R..*

**For further details, pls refer to the following page(s).*

Per Lundmark
ITCS Managing Director

Fay Wang
Lab Manager
Approved Signatory

The test results exclusively relate to the samples under test sent by customer.

The test report shall not be reproduced except in full, without the written approval of our laboratory.

The test report is not to prove to the society, as well as import & export commodity inspection in China.





1. Tests according to IOS-MAT-0079: AA-336472-8, 1.4 Quality (Q) requirements

Test Methods	Requirements (Level 1)		Test results	
Maintainability, IOS-TM-0012:AA-392032-2 Assessment according to ISO 105-A02:1993	Colour change minimum 3-4; Colour change on light colours after coffee and red wine test: minimum 2-3;	After cleaning	Ketchup	4-5
			Oil	4-5
			Coffee	4-5
			Soiling cloth	4-5
			Red wine	4-5
	After polishing	Ketchup	4-5	
		Oil	4-5	
		Coffee	4-5	
		Soiling cloth	4-5	
		Red wine	4-5	
			+	

Remark

Conditioning: Where necessary, the sample was conditioned and tested at a temperature of (23±2)°C and relative humidity of (50±5)% as specified in the requirements of EN ISO 2419:2012 (leather).

Key to grey scale ISO 105-A02 and ISO 105-A03:

- 5 - No change in appearance
- 4 - Slight change in appearance
- 3 - Moderate change in appearance
- 2 - Marked change in appearance
- 1 - Very marked change in appearance

-----End of Report-----

